
# FORTIDE®-HT

#### Product information



## Two-component epoxy coating for high operating temperatures



#### Specific advantages:



For operating temperatures up to +150  $^{\circ}$ C (+302  $^{\circ}$ F).



Fulfils ISO21809-3, type 18-A.



Free from volatile solvents and isocyanates.



Brush or spray application



Excellent cathodic disbondment resistance.

#### Product description

FORTIDE®-HT is a durable corrosion prevention system for buried and submerged pipelines which has been specifically designed for use in high temperature ranges.

FORTIDE®-HT features **outstanding hardness** while also providing **good abrasion resistance**.

FORTIDE®-HT covers a very broad range of applications,

thanks to its ease of use in a variety of ways.

The product is available in both spray and brush variants.

The isocyanate- and solvent-free system ensures compliance with the most stringent environmental and health and safety requirements.

FORTIDE®-HT fulfils the requirements of ISO 21809-3, type 18A.

The coating's durability is a result of its outstanding temperature resistance, excellent resistance to cathodic disbondment combined with exceptional indentation strength.

FORTIDE®-HT is available in different package sizes, which means that a practical and economical size is available depending on the requirements of the project.



## Typical product properties

Property		Unit	Typical value	Required value	Test method	
Туре		-	two components	-		
Colour		-	red brown	-		
Recommended minimum layer thickness		μm	≥ 750	-		
Theoretical consumption for 750 µm DFT		kg/m²	1.03	_		
		l/m²	0.76	-		
Indentation resistance (10 N/mm², stamp-ø 1.8mm)	+150 °C (+302 °F)	% of the original thickness	≤ 10	≤ 30		
Cathodic disbondment	+23 °C (+73 °F)	m.m	≤ 2	≤ 8	ISO 21809-3	
	+95 °C (+203 °F)	mm	≤ 5	≤ 15		
Hardness	+23 °C (+73 °F)	Shore D	≥ 80	-		
Adhesion	EP on steel		≥ 15	≥ 10		
	EP on EP	MPa				
Adhesion after hot water immersion		iviPd	≥ 11	≥ 7		
(28 d / +95 °C / +203 °F)	EP on EP		≥ 11	≥ 2		

## **Processing conditions**

Brush application				
Ambient and substrate temperature approx.		+10 °C (+50 °F)	+20 °C (+68 °F)	+40 °C (+104 °F)
Small package (brush variant)	Pot life (250 g total mass)	approx. 2 h	approx. 30 min.	approx. 18 min.
	Tack-free	approx. 5 h	approx. 2 h	approx. 45 min.
	durable	approx. 24 h	approx. 8 h	approx. 1.5 h
Hot airless spray applica	tion			
Ambient and substrate temperature approx.		+10 °C (+50 °F)	+20 °C (+86 °F)	+55 °C (+131 °F)
Hobbock (hot airless spraying)	Tack-free	approx. 4 h	approx. 1.5 h	approx. 30 min.
	durable	approx. 16 h	approx. 5 h	approx. 1 h
General processing cond	itions			
Processing temperature	Substrate	$\geq$ +10 °C ( $\geq$ +50 °F); min. +3 °C (+5.4 °F) above the dew point		
	Environment	-40 °C to +50 °C (-40 °F to +122 °F)		
Steel surface	Degree of cleanliness (ISO 8501-1)	min. Sa 2 ½		
	surface roughness (ISO 8503-1)		40 – 100 μm	
Relative humidity		≤ 80 %		

## Ordering information and packaging

Product name	Component	Contents per package approx.		Content per box
	Packaging	[1]	[kg]	[pcs.]
FORTIDE®-HT 0.8 I Kit	Comp. A / B (cans)	0.6 / 0.2	0.9 / 0.2	12 / 12
FORTIDE®-HT 1.2 l Kit	Comp. A / B (cans)	0.9 / 0.3	1.3 / 0.3	8 / 8
FORTIDE®-HT	Comp. A / B (hobbock)	29 / 29	42 / 30	-
	Comp. A / B (barrel)	207 / 207	298 / 213	-

#### Storage

FORTIDE®-HT can be stored in its unopened original packaging for at least 12 months from the date of manufacture. Storage temperature: +5 °C (+41 °F) to +30 °C (+86 °F). Store in a dry and frost-free location.