
SEALID[®]-Tape

Product information





Corrosion and mechanical protection in a single product with just one wrapping process.

Primer-free, solvent-free and environmentally friendly.

For operating temperatures up to +70°C (+158°F).

Fulfils the requirements of ISO 21809-3 Type 12A-2 at +70°C (+158°F), with just a 2-ply application (in a single wrapping process).

Fulfils the requirements of EN 12068-C 50 and DIN 30672-C 50 in a single wrapping process.

Primer-free all-in-one solution for permanent corrosion prevention of steel pipes and pipelines at operating temperatures up to +70°C (+158°F).

Connection layer (co-extruded)

Carrier layer Intermediate layer (co-extruded)

SEALID layer

Product description

SEALID[®]-Tape is a patented global innovation.

Secure corrosion prevention and also standards and differs from all existing solutions.

The resulting benefits are significant:

- 1. Cost saving due to faster work speed with a reduced number of work steps.
 - a. No primer
 - b. No (air-)drying
 - c. One single wrapping process
- 2. Cost saving because of the ease of transport, storage and application as no hazardous substance requirement needs to be met.

3. Elimination of risks to health and environmental as the product is solvent-free.


SEALID[®]-Tape has outstanding surface wetting characteristics. The two layers of the spiral-wrapped tape quickly fuse together and form a closed and durable protective hose. The system is impermeable for water vapour and oxygen and it is resistant against soil bacteria and soil electrolytes.

The product is also distinguished by exceptional properties such as minimised cathodic disbondment together with an extremely high peel and lap shear strength. SEALID[®] tape is manufactured using real multi-layer coextrusion. When spirally wrapped on the pipe, the SEALID[®] coating amalgamates with the connection layer to form a continuously closed hose-type coating of outstanding durability and resistance.

A single wrapping process (50% overlap) is enough to fulfil the requirements of ISO 21809-3 at operating temperatures of up to +70°C (+158°F). The requirements of EN 12068 and DIN 30672 for class C50 are also met with a single wrapping process (67% overlap).

The product can easily be applied by hand or using modern wrapping devices.

SEALID[®]-Tape is compatible with PE, PP, FBE, PU and bitumen factory coatings.



SEALID[®]-Tape All-in-1

long-term protection against mechanical loads are ensured with one single product without primer, extensive surface preparation or additional application tools. SEALID[®]-Tape fulfils the world's leading



Property		Unit	Typical value	Test method	
Outside colour		-	white	-	
Inside colour		-	green	-	
Total thickness		mm	≥ 1.30		
Outside adhesive layer thickness		mm	≥ 0.08	ISO 4591	
Carrier film thickness		mm	≥ 0.38	ASTM D1000	
Inside adhesive layer thickness		mm	≥ 0.84		
Elongation at break		%	600		
Tear resistance	ar resistance +23°C (+73°F)		140	EN 12068	
Electrical insulation resistance		Ωm^2	$\geq 10^{10}$		
Dielectric strength		kV/mm	≥ 40	DIN 53481	
Water absorption	+23°C (+73°F) 1 day/30 days	%	≤ 0.1 / ≤ 0.4	DIN 53495 ASTM D570	
Brittleness temperature		0.C (0.F)	-46±4 (-50.8±7.2)	DIN 53372	
		°C (°F)	-58±4 (-72.4±7.2)	GOST 10354	

Property	Test temperature	Unit	Typical value 2-ply 3-ply		Test method	
Impact resistance	+23°C (+73°F)	J/mm	≥ 4.0	≥ 5.0		
Indentation resistance (residual layer thickness)	+70°C (+158°F)	mm	≥ 0.65	≥ 1.0		
Cathodic disbondment resistance	+23°C (+73°F)	mm	≤ 10		ISO 21809-3	
Peel strength (inner layer/outer layer)	+23°C (+73°F)	N/cm	≥ 30			
Peel strength (steel surface)	+23°C (+73°F)	N/cm	≥ 15			
Lap shear strength	+23°C (+73°F)	N/cm ²	≥ 8			
Lap shear strength	+70°C (+158°F)	IN/CITI	≥ 3			

SEALID[®] Tape is easy to apply by hand. Application is even more efficient when using original **DEKOMAT**[®] wrapping devices. For **SEALID**[®] Tape with widths > 50 mm we recommend using the **DEKOMAT**[®] wrapping device to ensure excellent application quality.

Ordering information and packaging

	Width	Length [m]	m²/ roll	Content per box			
	[mm]			Rolls	m²	m	kg (approx.)
SEALID [®] -Tape Kern Ø 41 mm	30	5	0,15	12	1,8	60	3
	50	10	0,5	12	6	120	10
	100		1,0	6	6	60	10
SEALID -Tape Rent @ 41 mm	50	20	1,0	8	8	160	13
	100		2,0	4	8	80	13
	150		3,0	4	12	80	20
SEALID [®] -Tape Kern Ø 78 mm	50	20	1,0	8	8	160	13
	100		2,0	4	8	80	13
	150		3,0	4	12	80	20

Additional lengths and widths are available on request.

Storage

When stored in its original, unopened packaging, **SEALID®-Tape** can be stored for at least 24 months after the manufacturing date. Storage temperature: $\leq +40$ °C ($\leq +104$ °F)

Store in a dry location and without any pressure on the front side.

More information:

DEKOTEC GmbH

Felderstrasse 24 | 51371 Leverkusen | Germany Phone: +49 214 2602-0 | info@dekotec.com www.dekotec.com Our product information, application recommendations and other printed publications provide advice to the best of our knowledge and indicate our level of knowledge at the time of printing. The content is not legally binding. Therefore, no liability is assumed for incorrect and missing advice. The applicator is obliged to check the suitability and possibility of application for the intended purpose. Unless otherwise specified, all of the brands named are trademarks, at least registered in Germany, which are protected by law. Only our general terms and conditions of sale, which you will find at www.dekotec.com, apply. This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation, the German text of the respective German product informations, shall be decisive. The legal relationship shall be governed by German law.